

PRODUCT DESCRIPTION

Oscar TFX SAE 75W85 API GL-5 is a fully synthetic low viscosity gear lubricant formulated from synthetic base oils and an advanced additive system.

APPLICATION

Oscar TFX SAE 75W85 API GL-5 provides excellent low temperature fluidity for safe lubrication during very low temperature transmission and transaxle startup, and also maintains a thick protective oil film during extremely hot operating conditions. Used in all synchronized and non-synchronized manual transmission types operating under heavy loads and at high speed in extremely low temperatures, where an API GL-5 and MB 235.7 oil are required.

PROPERTIES

- Fuel economy feature thanks to low viscosity properties
- Exceptional thermal stability
- Enhanced frictional properties
- Resistance to high temperature oxidation
- Outstanding protection against low speed/high torque wear

PERFORMANCE LEVELS

Meets and exceeds:

API GL-5, MB 235.7, ZF TE-ML 18, VW TL 521 45-X (G 052 145 A1), VW TL 521 90 (G 052 190 A2/ G 055 190 A2)

TYPICAL PROPERTIES

| PARAMETERS | TEST METHOD | UNIT | Oscar TFX |
|------------------------|-------------|------|-----------|
| Viscosity Grade | | | 75W85 |
| Density @ 15°C, kg/l | ASTM D1298 | kg/l | 0.870 |
| Viscosity @ 100°C, cSt | ASTM D445 | cSt | 11.8 |
| Viscosity @ 40°C, cSt | ASTM D445 | cSt | 69.5 |
| Viscosity Index (min) | ASTM D2270 | - | 165 |
| Pour Point, °C | ASTM D97 | °C | -43 |
| Flash Point, °C | ASTM D92 | °C | 210 |

The values shown above are typical values at the date of publication. Oscar Lubricants reserves the right to change these typical values without prior notice

HEALTH & SAFETY, ENVIRONMENT:

Prolonged and repeated contact with oil may cause skin disorders. Avoid contact. Wash immediately with soap and water. Do not discharge used oil in to drains or the environment. Dispose to an authorized used oil collection point. For further Information on Safety Guidelines please refer to MSDS available on our website www.oscarlubricants.com